

CW-325

Engineering & Technical Data
June 2007

Construction: Single-ply acrylic coated polyester fabric hose construction reinforced with a spring steel wire helix.

Product Features:

- * Ideal for air & fume handling applications with temperatures up to 325 Fahrenheit
- * Excellent choice for overhead vehicle exhaust systems
- * Light weight and flexible
- * Listed as a UL 94 V-0 flame retardant
- * Available with an external wearstrip (CW-325-W)

Applications: Recommended for industrial air movement and fume control applications.

Temperature Range: - 20 F to + 325 F

Sizes I.D. (inches): 1.5, 2, 2.5, 3, 3.5, 4, 4.5, 5, 5.5, 6, 7, 8, 9, 10, 12, 14, and 16 Inch I.D.

ID Tolerances: To 8 Inch: -0.00 to + 0.125 Inch
8 Inch and over: - 0.00 to + 0.250 Inch


Standard Length: 25 Feet

Standard Colors: Black

End Finish: Plain Cut (cuffs available)

Markets: Air Duct Cleaning, Automotive, Chemical Fumes, Diesel/Engine Exhaust, Dry Cleaning, Dryer Hose, Exhaust Systems, Flame Retardant, Fume Exhaust, Garage Exhaust, High Temperature Applications, Glass Drying, Jet Fuel Vapor Venting, Landfill Venting, Ozone, Paper Mills, Plastics Industry, Pollution Control, Vehicle Exhaust Systems, Welding

Rubber-Cal, Inc.
3012 S. Croddy Way,
Santa Ana, CA 92704
800-370-9152
www.ducting.com



Ducting
.com

CW-325

Engineering & Technical Data
June 2007

Size Inside Diameter (Inches)	Approximate Weight Lbs./ft.	Min Centerline Bend Radius (Inches)	Compression Ratio	Max Recommended Negative Pressure (IN./HG)	Max Recommended Positive Pressure (PSI)
2	0.25	1.6	4 to 1	29	30
2.5	0.26	1.78	4 to 1	29	30
3	0.28	2.3	5 to 1	29	30
4	0.41	2.8	5 to 1	29	18
5	0.6	3.5	5 to 1	16	14
6	0.69	3.8	6 to 1	14	7
8	0.92	5.2	6 to 1	7	5
10	1.1	6.4	6 to 1	6	4
12	2	8	6 to 1	5	3.7

Note: Technical data based on 2 ft. straight lengths of hose 72 F.

Disclaimer: The proper use and maintenance of the hose and/or duct is the sole responsibility of the purchaser and ultimate user of the product. This information is presented as a general guide only. The number of variables which can be present in any application make firm recommendations impossible. Adequate testing under actual service conditions is necessary to properly establish suitability. We take pride in the quality of all of our products and we welcome comments and suggestions from our customers.

Rubber-Cal, Inc.
3012 S. Croddy Way,
Santa Ana, CA 92704
800-370-9152
www.ducting.com

