


Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Acetaldehyde	D	C	D	A	ND	A	D	ND	C	B	B	A	A
Acetamide	A	C	B	A	ND	B	D	ND	ND	ND	ND	ND	A
Acetate Solvents	D	D	D	A	D	ND	ND	ND	C	ND	ND	ND	A
Acetic Acid, Glacial	C	D	C	A	D	B	D	A	ND	ND	ND	ND	A
Acetic Acid, 5%	B	A	A	A	A	A	D	A	A	A	ND	A	A
Acetic Acid, 10%	B	A	B	A	B	A	D	A	A	A	A	A	A
Acetic Acid, 20%	B	A	B	A	B	A	D	A	A	A	ND	A	A
Acetic Acid, 30%	B	C	B	A	ND	A	D	A	A	A	ND	A	A
Acetic Acid, 50%	B	C	C	A	ND	B	D	A	A	A	ND	A	A
Acetic Acid, 80%	B	C	ND	A	ND	ND	ND	A	A	A	ND	A	A
Acetic Anhydride	D	C	A	A	ND	C	D	A	C	ND	C	A	A
Acetone	D	C	C	A	D	B	D	A	C	B	A	A	A
Acetone Cyanhydrin	D	B	C	A	ND	A	D	ND	ND	ND	ND	ND	ND
Acetonitrile	C	C	B	A	ND	ND	ND	ND	ND	ND	A	A	A
Acetophenone	D	D	D	A	ND	D	D	ND	ND	ND	ND	A	A
Acetyl Acetone	D	D	D	A	ND	D	C	ND	ND	ND	ND	ND	ND
Acetyl Chloride	D	D	D	A	ND	C	D	ND	C	ND	ND	A	A
Acetylene	B	C	C	A	ND	B	A	ND	A	ND	A	A	A
Acetylene Dichloride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Acrolein	B	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Acrylonitrile	D	D	C	A	ND	D	ND	A	C	ND	ND	ND	ND
Adipic Acid	B	D	ND	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Alcohol, Allyl	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Alcohol, Amyl	B	A	B	A	ND	D	D	B	C	A	ND	ND	A
Alcohol, Benzyl	D	C	B	A	D	ND	D	ND	ND	ND	ND	ND	A
Alcohol, Butyl	C	A	A	A	ND	B	D	ND	A	A	ND	ND	ND
Alcohol, Diacetone	D	C	B	A	ND	B	C	ND	ND	ND	ND	ND	ND
Alcohol, Furfuryl	D	D	D	A	ND	D	D	ND	ND	D	ND	ND	ND
Alcohol, Isopropyl	B	B	A	A	A	A	D	A	A	ND	ND	ND	ND
Alcohol, Methyl	A	A	A	A	A	A	D	A	A	A	ND	ND	ND
Alcohol, Octyl	B	B	A	A	ND	B	D	ND	ND	ND	ND	ND	ND
Alcohol, Propargyl	ND	ND	ND	ND	ND	ND	ND	ND	A	A	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Alcohol, Propyl	A	A	A	A	ND	A	D	ND	A	A	ND	ND	ND
Alcohols, Ethyl	A	A	A	A	A	A	D	A	A	ND	ND	ND	ND
Allyl Bromide	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Allyl Chloride	D	D	D	A	ND	ND	ND	ND	C	ND	ND	ND	ND
Aluminum Acetate	B	B	B	A	ND	D	D	ND	ND	ND	ND	ND	ND
Aluminum Chloride	A	A	A	A	ND	B	B	A	A	A	A	C	C
Aluminum Fluoride	A	A	A	A	ND	B	C	ND	A	A	ND	ND	B
Aluminum Hydroxide	B	A	B	A	ND	ND	ND	A	A	A	ND	ND	A
Aluminum Nitrate	A	B	A	A	ND	B	D	ND	A	ND	ND	ND	ND
Aluminum Oxochloride	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Aluminum Phosphate	A	A	A	A	ND	A	ND	A	ND	ND	ND	ND	ND
Aluminum Sulfate	B	A	A	A	ND	A	D	A	A	A	C	A	ND
Amino Ethyl Ethanol Amine	B	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Ammonia, anhydrous	C	A	C	A	ND	C	D	ND	ND	ND	ND	A	A
Ammonia, aqueous	A	ND	ND	A	A	ND	ND	A	A	ND	B	A	A
Ammonia, gas-cold	A	A	A	A	ND	A	A	A	A	ND	ND	ND	ND
Ammonia, gas-hot	D	B	B	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Ammonia, liquid	A	ND	ND	A	ND	ND	ND	A	ND	ND	ND	ND	ND
Ammonium Bicarbonate	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Ammonium Carbonate	D	B	B	A	ND	B	ND	A	A	A	ND	ND	B
Ammonium Chloride	B	A	A	A	ND	A	A	A	A	A	ND	ND	B
Ammonium Fluoride	B	B	ND	A	ND	ND	ND	ND	A	A	ND	ND	ND
Ammonium Hydroxide	D	B	A	A	A	A	A	A	A	ND	ND	B	A
Ammonium Hydroxide, 3 molar	A	A	A	A	ND	A	D	ND	ND	ND	ND	ND	ND
Ammonium Hydroxide, concentrate	D	A	A	A	ND	A	D	ND	ND	ND	ND	ND	ND
Ammonium Metaphosphate	B	B	B	A	ND	ND	ND	ND	A	A	ND	ND	ND
Ammonium Nitrate	A	B	A	A	ND	B	D	A	A	A	ND	ND	A
Ammonium Nitrite	B	A	A	A	ND	B	ND	ND	ND	ND	ND	ND	ND
Ammonium Persulfate	D	C	A	A	ND	ND	D	ND	A	ND	ND	ND	A
Ammonium Phosphate	A	A	A	A	ND	A	ND	A	A	ND	ND	ND	ND
Ammonium Phosphate, dibaic	A	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	C
Ammonium Phosphate, monobasic	A	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	C




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Ammonium Phosphate, tribasic	A	C	A	A	ND	A	ND	ND	ND	ND	ND	ND	A
Ammonium Salts	A	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Ammonium Sulfate	B	A	A	A	A	A	A	A	A	A	ND	ND	B
Ammonium Sulfide	A	A	A	A	ND	ND	ND	ND	A	A	ND	ND	A
Ammonium Sulfite	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Ammonium Thiocyanate	A	A	A	A	ND	ND	ND	ND	A	A	ND	ND	ND
Ammonium Thiosulfate	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Amyl Acetate	D	D	D	A	D	D	D	A	C	B	B	B	A
Amyl Acetone	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Amyl Borate	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Amyl Chloride	D	D	D	A	ND	D	ND	A	C	ND	ND	ND	ND
Amyl Chloronaphthalene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Amyl Napthalene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Amyl Oleate	A	ND	D	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Amyl Phenol	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Amylamine	C	D	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Anethole	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Aniline	D	D	D	A	ND	D	D	A	C	A	B	A	A
Aniline Chlorohydrate	ND	ND	ND	ND	ND	ND	ND	ND	C	ND	ND	ND	ND
Aniline Dyes	D	B	B	A	ND	C	D	ND	ND	ND	ND	ND	ND
Aniline Hydrochloride	C	D	D	A	ND	D	D	ND	C	ND	ND	ND	ND
Animal Fats	A	B	B	A	ND	D	B	ND	ND	ND	ND	ND	ND
Ansul Ether	C	D	D	A	ND	D	B	ND	ND	ND	ND	ND	ND
Anthraquinone	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Anthraquinone Sulfonic Acid	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Antimony Chloride	B	ND	ND	A	ND	ND	ND	ND	ND	A	ND	ND	ND
Antimony Pentachloride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Antimony Pentaculcride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Antimony Trichloride	A	ND	ND	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Aqua Regia	D	D	D	A	D	D	D	ND	ND	B	ND	ND	D
Aromatic Hydrocarbons	C	D	D	A	C	D	D	ND	ND	ND	ND	ND	ND
Arsenic Acid	B	B	A	A	ND	A	C	A	A	A	ND	ND	B




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Arsenic Chloride	C	B	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Arsenic Trichloride	C	B	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
ASTM Oil #1	A	A	B	A	A	A	A	C	ND	ND	ND	ND	ND
ASTM Oil #2	A	B	D	A	A	D	B	ND	ND	ND	ND	ND	ND
ASTM Oil #3	A	C	C	A	A	C	B	C	ND	ND	ND	ND	ND
ASTM Oil #4	B	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
ASTM Reference Fuel A	A	B	C	A	A	D	A	B	ND	ND	ND	ND	ND
ASTM Reference Fuel B	A	D	D	A	ND	D	B	C	ND	ND	ND	ND	ND
ASTM Reference Fuel C	B	D	D	A	ND	D	D	C	ND	ND	ND	ND	ND
Barium Carbonate	A	A	A	A	ND	ND	ND	ND	A	A	ND	ND	B
Barium Chloride	A	A	A	A	ND	A	A	ND	A	A	ND	B	B
Barium Hydroxide	A	A	A	A	ND	A	B	A	A	A	B	A	A
Barium Salts	A	A	A	A	ND	A	A	ND	ND	ND	ND	ND	ND
Barium Sulfate	A	A	B	A	A	A	A	ND	A	A	A	A	A
Barium Sulfide	A	A	A	A	ND	A	A	ND	A	A	ND	ND	A
Benzaldehyde	D	D	D	A	ND	D	D	ND	C	C	ND	ND	A
Benzene	D	D	D	A	D	D	D	C	C	B	A	A	B
Benzene Sulfonic Acid	C	B	B	A	ND	D	D	ND	A	A	C	A	ND
Benzene Sulfonic Acid, 10%	D	B	A	A	ND	D	D	ND	ND	ND	ND	ND	ND
Benzoic Acid	D	C	B	A	ND	B	D	A	A	A	ND	ND	B
Benzoic Aldehyde	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Benzol	D	D	D	A	ND	D	D	ND	C	ND	ND	ND	ND
Benzotrichloride	D	ND	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Benzoyl Chloride	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Benzyl Acetate	D	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Benzyl Chloride	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Bismuth Carbonate	A	ND	A	A	ND	ND	ND	ND	A	A	ND	ND	ND
Blast Furnace Gas	D	D	C	A	ND	A	D	ND	ND	ND	ND	ND	ND
Bleach Solutions	D	C	A	A	C	B	D	ND	ND	ND	ND	ND	ND
Borax	B	C	A	A	ND	B	A	A	A	ND	B	A	A
Boric Acid	C	C	A	A	A	A	A	A	A	A	ND	ND	B
Brine	A	A	A	A	A	A	A	ND	A	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Bromic Acid	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Bromine	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Bromo Benzene	D	D	D	A	ND	D	D	ND	C	ND	ND	ND	ND
Butadiene	D	D	D	A	ND	ND	D	D	A	ND	A	A	A
Butane	A	A	B	A	ND	D	C	A	A	ND	A	A	A
Butanediol	A	ND	ND	A	ND	ND	ND	A	ND	A	ND	ND	ND
Butanol, primary	A	A	A	A	ND	B	D	ND	A	ND	ND	ND	ND
Butanol, secondary	B	B	A	A	ND	A	D	ND	A	ND	ND	ND	ND
Butyl Acetate	D	D	D	A	D	D	D	A	A	A	A	A	ND
Butyl Acrylate	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Amine	C	D	D	A	ND	B	D	ND	ND	ND	A	A	A
Butyl Benzene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Bromide	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Butyrate	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Carbitol	C	B	B	A	D	B	ND	ND	ND	ND	ND	ND	ND
Butyl Cellosolve	C	C	B	A	D	ND	D	ND	A	ND	ND	ND	ND
Butyl Chloride	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Ether	B	C	C	A	ND	D	B	ND	ND	ND	A	A	A
Butyl Ethyl Acetaldehyde	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Ethyl Ether	B	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Oleate	D	D	D	A	ND	B	ND	ND	ND	ND	ND	ND	ND
Butyl Phenol	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Butyl Phthalate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Butyl Stearate	B	D	D	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Butylene	B	C	C	A	ND	D	D	ND	A	ND	A	A	A
Butyraldehyde	D	D	D	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Butyric Acid	D	C	C	A	ND	ND	ND	A	A	B	ND	ND	B
Butyric Anhydride	C	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Calcium Acetate	B	B	B	A	ND	D	D	ND	ND	ND	ND	ND	ND
Calcium Bisulfate	A	A	A	A	ND	B	A	ND	ND	ND	ND	ND	ND
Calcium Bisulfite	A	A	A	A	ND	A	A	ND	A	ND	ND	ND	ND
Calcium Carbonate	A	A	A	A	ND	A	C	ND	A	A	ND	ND	A




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Calcium Chlorate	A	C	A	A	ND	ND	ND	ND	A	A	ND	ND	ND
Calcium Chloride	B	A	A	A	A	A	A	A	A	A	C	B	B
Calcium Hydroxide	B	C	A	A	ND	A	C	A	A	A	ND	ND	A
Calcium Hypochlorite	D	D	A	A	ND	B	D	A	A	A	ND	ND	C
Calcium Nitrate	B	A	A	A	ND	B	A	A	A	A	ND	ND	ND
Calcium Phosphate	A	B	A	A	ND	A	A	ND	ND	ND	ND	ND	ND
Calcium Salts	A	A	A	A	A	B	A	ND	ND	ND	ND	ND	ND
Calcium Sulfate	A	C	A	A	ND	ND	ND	ND	A	A	B	A	A
Calcium Sulfide	B	B	A	A	ND	B	A	ND	ND	ND	ND	ND	ND
Calcium Sulfite	A	A	A	A	ND	A	A	ND	ND	ND	ND	ND	ND
Caprylic Acid	C	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Carbinol	A	A	A	A	ND	A	D	ND	ND	ND	ND	ND	ND
Carbitol	B	B	B	A	D	B	D	ND	A	ND	ND	ND	ND
Carbitol Acetate	C	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Carbolic Acid	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	A
Carbon Bisulfide	D	D	D	A	ND	C	C	ND	C	ND	ND	ND	ND
Carbon Dioxide	A	B	A	A	A	A	A	A	A	A	A	A	A
Carbon Disulfide	D	D	D	A	ND	C	C	D	ND	ND	ND	ND	ND
Carbon Monoxide	A	B	A	A	ND	A	A	A	A	A	ND	ND	A
Carbon Tetrachloride	C	D	D	A	D	D	D	ND	A	C	C	C	A
Carbon Tetrafluoride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Carbonic Acid	B	A	A	A	ND	A	A	ND	A	A	ND	ND	B
Caustic Potash	C	B	A	A	D	B	B	A	A	ND	ND	ND	ND
Caustic Soda	C	B	B	A	D	B	B	A	A	ND	ND	ND	ND
Cellosolve	D	D	B	A	D	D	D	ND	A	ND	A	A	ND
Cellulose Acetate	B	B	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Cellulube	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Chloracetic Acid	D	D	D	A	ND	ND	D	A	ND	ND	ND	ND	ND
Chlorinated Hydrocarbons	D	D	D	A	D	ND	ND	ND	ND	ND	ND	ND	ND
Chlorinated Solvents, wet or dry	D	D	D	A	D	D	D	ND	ND	ND	ND	ND	ND
Chlorine Dioxide	D	D	C	A	ND	C	D	ND	ND	ND	ND	ND	ND
Chlorine Gas, dry	D	C	D	A	ND	ND	ND	C	ND	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Chlorine Gas, wet	D	D	D	A	ND	ND	ND	C	ND	ND	ND	ND	ND
Chlorine Water, saturated	D	D	B	A	ND	ND	ND	C	A	A	ND	ND	ND
Chloro Acetone	D	C	C	A	ND	D	D	ND	ND	ND	ND	ND	ND
Chloro Benzene	D	D	D	A	ND	D	D	C	ND	ND	ND	ND	ND
Chloro Butadiene	D	D	C	A	ND	D	D	ND	ND	ND	ND	ND	ND
Chloro Butane	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Chloro Pentane	D	D	D	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Chloro Phenol	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Chloro Prene	D	D	C	A	ND	D	D	ND	ND	ND	ND	ND	ND
Chloro Propanone	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Chloro Toluene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Chloroform	D	D	D	A	ND	D	D	D	ND	ND	ND	ND	ND
Chlorosulfonic Acid	D	D	D	A	ND	D	D	B	ND	ND	ND	ND	ND
Chlorothene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Chrome Alum	A	A	A	A	ND	A	ND	A	A	A	ND	ND	ND
Chromic Acid	D	D	B	A	ND	C	D	ND	ND	ND	ND	ND	ND
Citric Acid	B	A	A	A	A	A	A	A	A	A	ND	ND	A
Cloric Acid, aqueous	D	ND	ND	A	ND	ND	ND	A	A	ND	ND	ND	ND
Cobalt Chloride	A	A	A	A	ND	B	D	ND	ND	ND	ND	ND	ND
Coke Oven Gas	D	C	B	A	ND	B	D	ND	A	ND	ND	ND	ND
Copper Arsenate	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Copper Chloride	A	D	A	A	ND	A	A	A	A	ND	ND	ND	C
Copper Cyanide	A	B	B	A	ND	A	A	ND	A	ND	ND	ND	A
Copper Nitrate	C	A	A	A	ND	ND	ND	ND	A	ND	ND	ND	A
Copper Nitrite	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Copper Salts	A	A	A	A	A	A	A	ND	A	ND	ND	ND	ND
Copper Sulfate	B	A	A	A	ND	A	A	A	A	ND	ND	C	A
Copper Sulfide	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Cotton Seed Oil	A	B	B	A	A	A	A	B	A	A	ND	A	A
Cresylic Acid	C	D	C	A	ND	D	D	ND	ND	ND	ND	ND	ND
Cresylic Acid, 50%	D	D	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	A
Crotonaldehyde	D	ND	D	A	ND	ND	ND	ND	D	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Cumene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Cupric Carbonate	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Cupric Chloride	A	B	A	A	ND	A	A	ND	ND	A	ND	ND	ND
Cupric Nitrate	A	A	A	A	ND	ND	ND	ND	ND	A	ND	ND	ND
Cupric Nitrite	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Cupric Sulfate	A	A	A	A	A	A	A	ND	A	A	ND	ND	ND
Cyclo Hexane	B	D	D	A	A	D	B	D	ND	C	A	A	A
Cyclo Hexanol	B	B	B	A	ND	D	C	C	D	ND	C	A	A
Cyclo Hexanone	D	D	D	A	ND	D	D	B	D	ND	A	A	A
Cyclo Pentane	B	A	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Decalin	D	D	D	A	ND	D	D	ND	D	ND	ND	ND	ND
Decane	B	D	D	A	ND	B	B	ND	ND	ND	ND	ND	ND
Decyl Alcohol	A	D	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Detergent, liquid	A	B	A	A	A	A	D	ND	A	ND	C	A	A
Diamyl Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dibenzyl Ether	D	D	D	A	ND	ND	B	ND	ND	ND	ND	ND	ND
Dibenzyl Sebecate	D	D	D	A	ND	C	C	ND	ND	ND	ND	ND	ND
Dibromo Benzene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dibromo Ethane	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Dibutyl Amine	D	D	D	A	ND	C	D	ND	ND	ND	ND	ND	ND
Dibutyl Ether	C	D	C	A	ND	D	B	ND	ND	ND	ND	ND	ND
Dibutyl Phthalate	D	D	D	A	C	B	C	A	D	ND	ND	ND	ND
Dibutyl Sebacate	D	D	D	A	ND	B	D	ND	B	ND	ND	ND	ND
Dicalcium Phosphate	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dichloro Acetic Acid	D	ND	D	A	ND	ND	ND	B	ND	ND	ND	ND	ND
Dichloro Benzene	D	D	D	A	ND	D	D	ND	D	ND	ND	ND	ND
Dichloro Butane	C	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Dichloro Ethane	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dichloro Ethyl Ether	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dichloro Ethylene	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dichloro Hexane	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dichloro Isopropyl Ether	D	D	D	A	ND	D	B	ND	ND	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Dichloro Methane	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Dichloro Pentane	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dichloro Propane	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dicyclo Hexyl Amine	C	D	D	A	ND	ND	D	ND	ND	ND	ND	ND	ND
Diesel Oil, light	A	B	B	A	ND	D	C	D	ND	ND	ND	ND	ND
Diethanol Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diethyl Amine	B	B	C	A	ND	B	C	ND	ND	ND	ND	ND	A
Diethyl Benzene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Diethyl Ether	D	C	C	A	ND	D	A	ND	D	ND	ND	ND	ND
Diethyl Ketone	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diethyl Oxalate	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diethyl Phthalate	D	C	D	A	B	ND	ND	ND	ND	ND	ND	ND	ND
Diethyl Sebecate	D	D	D	A	ND	B	D	A	ND	ND	ND	ND	ND
Diethyl Sulfate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diethyl Triamine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diethylene Dioxide	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Diethylene Glycol	A	A	A	A	ND	B	D	ND	ND	A	ND	ND	A
Diethylene Glycol-Monobutyl Ether	A	B	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Diethylene Glycol-Monoethyl Ether	B	B	B	A	ND	B	D	ND	ND	ND	ND	ND	ND
Diethylene Triamine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diglycolic Acid	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Dihydroxy Ethyl Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Butylene	B	D	D	A	ND	D	D	ND	ND	ND	A	A	A
Diiso Decyl Adipate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Decyl Phthalate	D	D	D	A	B	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Octyl Adipate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Octyl Phthalate	D	ND	D	A	B	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Propanol Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Propyl Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Propyl Benzene	D	D	D	D	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Propyl Ether	B	D	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diiso Propyl Ketone	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Diisobutyl Ketone	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dilauryl Ether	B	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dimethyl Amine	D	ND	D	A	ND	ND	ND	B	A	ND	ND	ND	ND
Dimethyl Aniline	D	D	D	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Dimethyl Benzene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Dimethyl Formamide	C	D	D	A	D	B	D	A	D	ND	A	A	A
Dimethyl Phthalate	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dimethyl Sulfate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dimethyl Sulfide	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dinitro Benzene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dinitro Toluene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Diocetyl Adipate	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diocetyl Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Diocetyl Phthalate	D	D	D	A	ND	C	D	B	D	B	A	A	A
Diocetyl Sebecate	D	D	D	A	ND	C	B	ND	ND	ND	ND	ND	ND
Dioxane	D	D	D	A	ND	D	D	ND	ND	ND	C	C	C
Dioxolane	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Dipentene	B	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Diphenyl	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Diphenyl Oxide	D	D	C	A	ND	C	ND	ND	ND	ND	ND	ND	A
Diphenyl Phthylate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dipropyl Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dipropyl Ketone	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dipropylene Glycol	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Disodium Phosphate	A	ND	A	A	ND	ND	ND	ND	A	A	ND	ND	ND
Divinyl Benzene	D	ND	D	A	ND	ND	ND	ND	D	ND	ND	ND	ND
Dodecyl Alcohol	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dodecyl Benzene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dodecyl Toluene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Dry Cleaning Fluids	C	D	D	A	C	D	D	ND	ND	ND	ND	ND	ND
Epichlorohydrin	D	D	D	A	ND	D	D	A	ND	ND	A	A	A
Ethanol	A	A	A	A	A	A	C	ND	A	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Ethylene Bromide	D	D	D	A	ND	D	D	ND	D	ND	ND	ND	ND
Ethylene Chloride	D	D	D	A	ND	C	D	D	D	ND	C	C	A
Ethylene Chlorohydrin	D	B	B	A	ND	C	D	ND	ND	ND	ND	ND	ND
Ethylene Diamine	C	A	B	A	ND	A	D	A	ND	ND	D	A	A
Ethylene Dibromide	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Ethylene Dichloride	D	D	D	A	ND	C	D	C	D	C	C	C	C
Ethylene Glycol	D	A	A	A	ND	A	B	A	A	A	D	A	A
Ethylene Glycol Monobutyl Ether	B	C	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Ethylene Glycol Monoethyl Ether Acetate	C	D	D	A	ND	C	D	ND	ND	ND	ND	ND	ND
Ethylene Oxide	D	D	D	A	ND	D	D	A	D	ND	ND	ND	ND
Fatty Acids	B	D	D	A	A	C	ND	B	A	A	ND	ND	A
Ferric Bromide	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Ferric Chloride	A	B	B	A	ND	B	A	A	A	A	D	D	D
Ferric Nitrate	A	A	A	A	ND	C	A	ND	A	A	ND	ND	B
Ferric Sulfate	B	A	A	A	ND	B	ND	ND	A	A	ND	ND	A
Ferrous Acetate	D	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Ferrous Chloride	A	B	B	A	ND	ND	ND	ND	A	A	D	D	D
Ferrous Hydroxide	B	ND	B	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Ferrous Sulfate	A	A	A	A	ND	ND	ND	ND	A	A	ND	ND	B
Flourine Gas, dry	D	D	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Flourine Gas, wet	D	D	D	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Fluoboric Acid	A	B	A	A	ND	ND	ND	ND	A	A	ND	ND	B
Fluoroboric Acid	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Fluosilicic Acid	A	A	A	A	ND	D	B	A	A	A	ND	ND	B
Formaldehyde	C	D	B	A	ND	B	D	A	A	A	B	B	A
Formamide	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Formic Acid	D	D	B	A	ND	B	D	A	C	A	ND	ND	A
Freon 11	B	D	A	A	ND	D	D	C	A	ND	A	A	A
Freon 112	B	B	B	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Freon 113	C	D	A	A	ND	D	B	C	B	ND	A	A	A
Freon 114	A	A	A	A	ND	D	A	C	ND	ND	A	A	A
Freon 114B2	B	A	A	A	ND	D	ND	ND	ND	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Glucose	A	A	A	A	ND	A	B	A	A	A	ND	ND	A
Glycerine	A	A	A	A	A	A	B	A	A	ND	A	ND	ND
Glycol	A	A	A	A	A	A	B	A	A	A	ND	ND	ND
Glycolic Acid	B	B	ND	A	ND	ND	ND	A	A	ND	D	A	A
Grease	A	D	C	A	A	ND	ND	ND	ND	ND	ND	ND	A
Heptanal	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Heptane	A	D	B	A	A	D	B	D	A	C	A	A	A
Heptane Carboxylic Acid	C	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Hexaldehyde	D	A	C	A	ND	B	B	ND	ND	ND	ND	ND	ND
Hexane	A	D	B	A	A	D	B	D	B	ND	A	A	A
Hexanol	A	B	B	A	ND	B	D	ND	A	ND	ND	ND	ND
Hexene	A	B	C	A	ND	D	A	ND	ND	ND	ND	ND	ND
Hexyl Amine	C	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Hexyl Methyl Ketone	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Hexylene	A	B	C	A	ND	D	A	ND	ND	ND	ND	ND	ND
Hexylene Glycol	A	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND
Hydraulic Oil (petroleum)	A	B	B	A	ND	C	A	ND	ND	ND	ND	ND	A
Hydro Quinone	D	D	C	A	ND	ND	ND	ND	A	A	ND	ND	ND
Hydrochloric Acid, 10%	C	A	A	A	A	C	B	A	A	ND	D	D	D
Hydrochloric Acid, 20%	D	C	A	A	ND	C	C	A	A	ND	D	D	D
Hydrochloric Acid, 25%	C	C	A	A	ND	C	D	A	A	ND	D	D	D
Hydrochloric Acid, 37%	D	C	A	A	ND	C	ND	A	A	ND	D	D	D
Hydrochloric Acid, 38%	C	C	A	A	ND	C	D	A	A	ND	D	D	D
Hydrochloric Acid, 40%	D	ND	A	ND	ND	ND	ND	ND	A	ND	D	D	D
Hydrochloric Acid, 50%	ND	ND	A	ND	ND	ND	ND	ND	A	ND	D	D	D
Hydrocyanic Acid	B	A	A	A	ND	B	C	A	A	A	ND	ND	A
Hydrocyanic Acid, 10%	B	A	A	ND	ND	B	ND	A	A	A	ND	ND	ND
Hydrofluoric Acid, 10%	B	A	A	A	ND	D	D	A	A	ND	ND	ND	ND
Hydrofluoric Acid, 20%	C	C	A	ND	ND	D	D	A	A	C	ND	ND	C
Hydrofluoric Acid, 48%	D	C	A	A	ND	D	D	A	A	ND	ND	ND	ND
Hydrofluoric Acid, 50%	C	C	A	A	ND	D	D	A	A	ND	D	D	C
Hydrofluoric Acid, 65%	D	C	A	A	ND	D	ND	A	A	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Iso Propanol Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isoamyl Acetate	D	D	C	A	ND	D	D	ND	ND	ND	ND	ND	ND
Isoamyl Alcohol	A	B	A	A	ND	D	C	ND	ND	ND	ND	ND	ND
Isoamyl Bromide	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isoamyl Butyrate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isoamyl Chloride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isoamyl Ether	B	D	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isoamyl Phthalate	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isobutane	A	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isobutanol	B	B	A	A	ND	A	D	ND	ND	ND	ND	ND	ND
Isobutyl Acetate	D	D	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isobutyl Alcohol	B	B	A	A	ND	A	D	ND	ND	ND	ND	ND	ND
Isobutyl Aldehyde	D	C	D	A	ND	C	C	ND	ND	ND	ND	ND	ND
Isobutyl Amine	D	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isobutyl Carbinol	A	B	A	A	ND	D	C	ND	ND	ND	ND	ND	ND
Isobutyl Chloride	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isobutyl Ether	B	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isobutylene	C	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isopropyl Acetate	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	B
Isopropyl Amine	D	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Isopropyl Benzene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Isopropyl Chloride	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Isopropyl Ether	B	D	D	A	ND	D	B	B	ND	ND	ND	ND	A
Isopropyl Toluene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Jet Fuels JP-3	B	D	D	A	ND	D	B	ND	A	ND	A	A	A
Jet Fuels JP-4	B	D	D	A	ND	D	B	C	A	ND	A	A	A
Jet Fuels JP-5	B	D	D	A	ND	D	B	ND	A	ND	A	A	A
Jet Fuels JP-6	A	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Kerosene	A	D	D	A	ND	D	B	C	A	B	A	A	A
Ketones	D	D	D	A	D	C	D	ND	ND	ND	A	A	A
Lacquers	D	D	D	A	D	D	D	ND	ND	ND	ND	ND	A
Lactic Acid	C	C	A	A	ND	A	ND	A	B	A	C	A	A




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Lauric Acid	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Lauryl Alcohol	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Lauryl Chloride	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Lead Acetate	B	B	C	A	ND	D	D	A	A	A	ND	ND	B
Lead Arsenate	ND	B	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Lead Nitrate	A	A	B	A	ND	B	ND	ND	A	ND	ND	ND	ND
Lead Sulfamate	B	A	A	A	ND	B	ND	ND	ND	ND	ND	ND	ND
Lead Sulfate	A	B	A	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Lead Tetraethyl	B	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Lime Sulfur, dry	D	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Lime Sulfur, wet	A	A	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Limonene	C	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Linoleic Acid	B	D	D	A	ND	B	ND	ND	A	ND	ND	ND	ND
Linseed Oil	A	B	B	A	ND	B	B	B	A	C	ND	ND	ND
Lubricating Oils	A	D	C	A	ND	C	B	C	A	D	A	A	A
Lye Solutions	B	B	A	A	ND	B	D	ND	A	ND	ND	ND	ND
Magnesium Acetate	D	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Magnesium Carbonate	A	A	A	A	ND	ND	ND	ND	A	A	ND	ND	A
Magnesium Chloride	A	A	A	A	ND	A	A	A	A	A	ND	ND	A
Magnesium Hydrate	B	B	A	A	ND	B	C	ND	ND	ND	ND	ND	ND
Magnesium Hydroxide	B	B	A	A	ND	B	C	A	A	A	C	A	A
Magnesium Nitrate	A	B	A	A	ND	ND	ND	ND	A	A	ND	ND	A
Magnesium Salts	A	A	A	A	ND	A	A	A	ND	ND	ND	ND	ND
Magnesium Sulfate	A	B	A	A	ND	A	ND	A	A	A	ND	ND	A
Maleic Acid	D	B	C	A	ND	ND	ND	ND	A	B	ND	ND	A
Maleic Anhydride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Malic Acid	D	B	B	A	ND	B	ND	ND	A	ND	ND	ND	ND
Manganese Salts	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Manganese Sulfate	A	A	A	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Manganese Sulfide	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Manganese Sulfite	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Mercuric Chloride	A	A	A	A	ND	A	ND	A	A	A	ND	ND	D




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Methyl Salicylate	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Methyl Sulfate	ND	C	ND	ND	ND	ND	ND	ND	C	ND	ND	ND	ND
Methylated Spirits	A	B	A	A	ND	A	D	ND	ND	ND	ND	ND	ND
Methylene Bromide	D	D	D	A	ND	ND	ND	ND	B	ND	ND	ND	ND
Methylene Chloride	D	D	D	A	D	D	D	D	D	C	ND	ND	A
Mineral Oils	A	D	D	A	A	B	A	C	A	C	A	A	A
Mono Chloro Benzene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Mono Ethanol Amine	D	D	D	A	ND	B	C	ND	ND	ND	ND	ND	ND
Mono Ethyl Amine	C	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Mono Methyl Ether	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Mono Vinyl Acetate	D	D	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Muriatic Acid	D	D	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Naphtha	C	D	D	A	B	D	C	C	A	C	A	A	A
Naphthalene	D	D	D	A	ND	D	B	C	A	C	A	A	B
Napthenic Acid	B	D	D	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Natural Gas	A	A	A	A	ND	A	B	ND	A	ND	ND	ND	ND
Neohexane	A	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Nickel Acetate	D	B	D	A	ND	D	D	ND	A	ND	ND	ND	ND
Nickel Chloride	A	B	A	A	ND	A	C	ND	A	A	ND	ND	C
Nickel Nitrate	A	B	A	A	ND	ND	A	ND	A	A	ND	ND	ND
Nickel Salts	A	B	A	A	ND	A	C	A	A	ND	ND	ND	ND
Nickel Sulfate	A	A	A	A	ND	A	C	A	A	A	ND	ND	B
Nitric Acid, 10%	D	B	A	A	ND	B	C	A	A	A	C	A	A
Nitric Acid, 20%	D	D	ND	ND	ND	ND	ND	A	A	A	ND	A	A
Nitric Acid, 25%	D	D	B	A	ND	C	C	A	A	A	ND	A	A
Nitric Acid, 30%	D	D	D	A	ND	ND	ND	A	A	A	D	A	A
Nitric Acid, 35%	D	D	B	A	ND	D	C	ND	A	C	ND	A	A
Nitric Acid, 40%	D	D	ND	ND	ND	ND	ND	ND	A	C	ND	ND	ND
Nitric Acid, 50%	D	D	C	A	ND	D	D	D	A	C	ND	ND	A
Nitric Acid, 60%	D	D	ND	A	ND	ND	ND	D	A	C	ND	ND	ND
Nitric Acid, 69%	D	D	C	A	ND	D	D	D	A	C	ND	ND	ND
Nitric Acid, 70%	D	D	D	A	ND	ND	ND	D	A	C	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Nitric Acid, 86%	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Nitric Acid, concentrate	D	D	C	A	ND	D	D	ND	D	D	C	A	A
Nitric Acid, dilute	D	B	A	A	ND	B	C	ND	ND	ND	ND	ND	ND
Nitric Acid, red fuming	D	D	D	A	ND	D	D	C	ND	ND	ND	ND	ND
Nitro Benzene	D	D	D	A	ND	D	D	A	D	D	A	A	B
Nitro Methane	D	C	C	A	ND	D	D	ND	ND	ND	ND	ND	ND
Nitro Propane	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Nitrogen Tetraoxide	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Nitrous Oxide	D	ND	A	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Octa Decanoic Acid	B	B	B	A	ND	B	A	ND	ND	ND	ND	ND	ND
Octane	D	D	D	A	B	D	D	A	ND	ND	ND	ND	ND
Octanol	B	B	A	A	ND	B	D	ND	ND	ND	ND	ND	ND
Octyl Acetate	D	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Octyl Amine	C	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Octyl Carbinol	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Octylene Glycol	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Oleic Acid	C	D	C	A	A	D	B	A	A	C	ND	ND	A
Oleum	D	D	D	A	ND	ND	ND	D	D	ND	ND	ND	A
Olive Oil	A	D	B	A	ND	D	A	ND	ND	ND	ND	ND	A
Ortho Dichloro Benzene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Oxalic Acid	C	B	B	A	ND	B	D	A	A	A	ND	ND	A
Oxygen, cold	B	B	B	A	ND	A	A	A	ND	ND	ND	ND	ND
Oxygen, hot	D	D	D	A	ND	B	D	A	ND	ND	ND	ND	ND
Ozone	D	B	A	A	ND	A	A	ND	A	C	ND	ND	ND
Palmitic Acid	A	B	C	A	ND	D	A	A	ND	ND	ND	ND	ND
Palmitic Acid, 10%	A	C	C	ND	ND	ND	ND	ND	A	B	ND	ND	ND
Palmitic Acid, 70%	A	C	C	ND	ND	ND	ND	ND	B	B	ND	ND	ND
Para Dichloro Benzene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Paraform Aldehyde	B	B	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
P-Cymene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Pentane	A	A	B	A	A	D	D	ND	ND	ND	ND	ND	ND
Pentanol	B	A	B	A	ND	D	D	ND	ND	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Pentanone	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Pentene	B	A	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Peracetic Acid	ND	ND	ND	ND	ND	ND	ND	ND	C	ND	ND	ND	ND
Perchloric Acid	D	A	B	A	ND	D	D	D	ND	ND	ND	ND	ND
Perchloric Acid, 10%	D	D	D	ND	ND	ND	ND	ND	A	A	ND	ND	ND
Perchloric Acid, 70%	D	D	D	ND	ND	ND	ND	ND	D	ND	ND	ND	ND
Perchloro Ethylene	D	D	D	A	ND	C	D	D	ND	ND	A	A	A
Petrol	A	B	D	A	ND	C	B	ND	ND	ND	ND	ND	ND
Petrolatum	A	B	B	A	A	D	A	ND	A	ND	ND	ND	A
Petroleum Ether	A	B	D	A	ND	D	B	ND	ND	ND	ND	ND	ND
Petroleum Naphtha	A	B	C	A	B	D	B	ND	ND	ND	ND	ND	ND
Petroleum Oil, above 250 F.	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Petroleum Oil, below 250 F.	A	B	B	A	B	B	B	ND	ND	ND	ND	ND	ND
Petroleum Oil, crude	A	B	B	A	ND	D	C	ND	ND	ND	ND	ND	ND
Phenol	D	D	C	A	ND	D	D	C	C	B	A	C	A
Phenol Sulfonic Acid	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Phenyl Chloride	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Phenyl Hydrazine	D	D	D	A	ND	ND	ND	ND	D	ND	ND	ND	ND
Phorone	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Phosgene, gas	D	C	ND	A	ND	ND	ND	ND	B	ND	ND	ND	ND
Phosgene, liquid	D	C	ND	A	ND	ND	ND	ND	D	ND	ND	ND	ND
Phosphate Esters	D	D	D	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Phosphoric Acid, 10%	C	B	A	A	ND	B	A	A	A	A	D	D	A
Phosphoric Acid, 20%	C	B	A	A	ND	B	A	A	A	A	D	D	A
Phosphoric Acid, 30%	C	B	A	A	ND	ND	ND	A	A	A	D	D	A
Phosphoric Acid, 40%	C	B	A	A	ND	ND	ND	A	A	A	D	D	A
Phosphoric Acid, 45%	C	B	B	A	ND	ND	A	ND	A	A	D	D	A
Phosphoric Acid, 50%	C	B	B	A	ND	D	A	ND	A	A	D	D	A
Phosphoric Acid, 80%	D	B	B	A	ND	ND	ND	C	A	ND	D	D	B
Phosphoric Acid, 85%	D	C	B	A	ND	D	A	ND	A	B	D	D	B
Phosphoric Acid, concentrate	D	D	C	A	ND	D	A	ND	ND	ND	ND	ND	ND
Phosphoric Acid, crude	C	C	A	A	ND	C	ND	ND	A	ND	D	D	C




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Potassium Bicarbonate	A	A	A	A	ND	ND	ND	ND	A	A	ND	ND	B
Potassium Bichromate	A	B	A	A	ND	A	B	ND	A	ND	ND	ND	ND
Potassium Bisulfate	A	A	A	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Potassium Bisulfite	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Potassium Borate	A	A	A	A	ND	ND	ND	A	A	A	ND	ND	ND
Potassium Bromate	A	A	ND	A	ND	ND	ND	A	A	A	ND	ND	ND
Potassium Bromide	A	A	ND	A	ND	ND	ND	A	A	A	ND	ND	B
Potassium Carbonate	A	A	A	A	ND	ND	ND	ND	A	A	ND	ND	A
Potassium Chlorate	D	C	A	A	ND	ND	ND	A	A	A	ND	ND	A
Potassium Chloride	A	A	A	A	ND	A	A	A	A	A	D	C	A
Potassium Chromate	B	A	C	A	ND	ND	ND	A	A	A	ND	ND	B
Potassium Cuprocyanide	A	A	A	A	ND	A	A	ND	ND	ND	ND	ND	ND
Potassium Cyanide	A	A	A	A	ND	A	A	A	A	A	ND	ND	A
Potassium Dichromate	A	B	A	A	ND	A	B	A	A	A	ND	ND	A
Potassium Ferricyanide	A	A	A	ND	ND	ND	A	ND	A	ND	ND	ND	ND
Potassium Fluoride	A	A	A	ND	ND	ND	ND	ND	A	A	ND	ND	ND
Potassium Hydrate	C	B	A	A	ND	B	B	ND	ND	ND	ND	ND	ND
Potassium Hydroxide	C	B	A	A	ND	B	B	A	A	A	D	C	B
Potassium Hypochlorite	D	D	B	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Potassium Nitrate	A	A	A	A	ND	A	A	A	A	A	ND	ND	B
Potassium Perborate	ND	C	ND	ND	ND	ND	ND	ND	A	A	ND	ND	ND
Potassium Permanganate	D	C	A	ND	ND	ND	ND	ND	A	A	ND	ND	B
Potassium Persulfate	ND	C	ND	ND	ND	ND	ND	ND	A	A	ND	ND	ND
Potassium Phosphate	ND	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Potassium Salts	A	A	A	A	ND	A	A	ND	ND	ND	ND	ND	ND
Potassium Silicate	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Potassium Sulfate	A	A	A	A	ND	A	A	ND	A	A	ND	ND	B
Potassium Sulfide	A	A	A	A	ND	A	A	ND	ND	A	ND	ND	ND
Potassium Sulfite	A	A	A	A	ND	A	ND	ND	ND	A	ND	ND	ND
Potassium Thiosulfate	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Producer Gas	A	B	B	A	ND	B	A	ND	ND	ND	ND	ND	ND
Propane	A	B	B	A	ND	D	C	D	A	ND	ND	ND	A




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Propanediol	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Propionaldehyde	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Propionic Acid	D	D	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Propyl Acetate	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Propyl Aldehyde	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Propyl Chloride	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Propylene Diamine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Propylene Dichloride	D	D	D	A	ND	ND	ND	ND	D	C	ND	ND	ND
Propylene Glycol	A	C	A	A	A	ND	ND	ND	ND	A	ND	ND	A
Propylene Oxide	D	D	D	A	ND	D	D	ND	D	ND	ND	ND	ND
Prussic Acid	B	B	A	A	ND	B	C	ND	ND	ND	ND	ND	ND
Pyranol	A	D	D	A	ND	D	B	ND	ND	ND	ND	ND	ND
Pyridine	D	D	D	A	ND	D	D	B	D	B	A	A	B
Pyroligneous Acid	D	C	C	A	ND	A	D	ND	ND	ND	ND	ND	ND
Pyrrole	D	D	D	A	ND	B	ND	ND	ND	ND	ND	ND	ND
Salicylic Acid	C	D	A	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Salt/Sea Water	A	A	A	A	ND	A	D	A	A	ND	ND	ND	A
Selenic Acid	ND	A	ND	ND	ND	ND	ND	ND	ND	B	ND	ND	ND
Sewage	A	B	A	A	ND	B	D	ND	ND	ND	ND	ND	ND
Silicate Esters	B	A	A	A	ND	D	A	ND	ND	ND	ND	ND	ND
Silicic Acid	A	A	A	A	ND	ND	ND	A	A	ND	ND	ND	ND
Silicone Oils & Greases	A	A	A	A	ND	C	A	C	A	ND	ND	ND	A
Silver Cyanide	ND	A	A	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Silver Nitrate	B	A	A	A	ND	A	A	A	A	A	ND	ND	A
Silver Salts	A	ND	ND	A	ND	ND	ND	A	ND	ND	ND	ND	ND
Soap Solutions	A	A	A	A	A	A	A	A	A	A	ND	ND	A
Sodium Acetate	B	B	B	A	ND	D	D	ND	A	A	ND	ND	B
Sodium Acid Sulfate	B	A	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Sodium Aluminate	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	A
Sodium Benzoate	ND	ND	ND	A	ND	ND	ND	ND	A	A	ND	ND	ND
Sodium Bicarbonate	A	A	A	A	ND	A	ND	A	A	A	ND	ND	A
Sodium Bisulfate	B	C	A	A	ND	A	ND	ND	A	A	ND	ND	A




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Sodium Bisulfite	A	A	A	A	ND	A	ND	ND	A	A	ND	ND	A
Sodium Borate	A	A	A	A	ND	A	ND	ND	A	A	ND	ND	ND
Sodium Bromide	ND	ND	ND	A	ND	ND	ND	ND	A	A	ND	ND	ND
Sodium Carbonate	A	A	ND	ND	ND	ND	ND	ND	A	A	ND	ND	A
Sodium Carbonate, anhydrous	A	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Sodium Carbonate, hydrated	A	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Sodium Carbonate, soda ash	A	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Sodium Chlorate	A	A	A	A	ND	A	ND	ND	A	A	ND	ND	B
Sodium Chloride	A	A	A	A	ND	A	A	A	A	A	C	C	B
Sodium Chromate	A	A	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Sodium Cyanide	A	A	A	A	ND	A	ND	ND	A	A	ND	ND	A
Sodium Dichromate	ND	B	B	A	ND	ND	A	A	A	A	ND	ND	ND
Sodium Ferricyanide	ND	ND	ND	ND	ND	ND	ND	ND	A	A	ND	ND	ND
Sodium Ferrocyanide	ND	ND	ND	ND	ND	ND	ND	ND	A	A	ND	ND	ND
Sodium Fluoride	A	A	ND	A	ND	ND	ND	ND	A	A	ND	ND	ND
Sodium Hydroxide	C	B	B	A	ND	B	B	ND	A	A	ND	ND	ND
Sodium Hydroxide, 3 molar	B	B	A	A	D	A	B	ND	ND	ND	ND	ND	ND
Sodium Hydroxide, 15%	A	A	A	A	D	ND	ND	ND	A	ND	D	B	A
Sodium Hydroxide, 20%	A	A	A	A	D	ND	ND	A	A	ND	D	B	B
Sodium Hydroxide, 30%	ND	A	A	A	D	ND	ND	ND	A	ND	D	B	B
Sodium Hydroxide, 50%	D	A	A	A	D	ND	ND	A	A	ND	D	B	B
Sodium Hydroxide, 70%	D	A	A	A	D	ND	ND	ND	A	ND	ND	ND	ND
Sodium Hydroxide, 73%	D	ND	ND	A	D	ND	ND	A	A	ND	ND	ND	ND
Sodium Hypochlorite, 5%	D	C	A	A	ND	B	D	A	A	ND	D	D	C
Sodium Hypochlorite, 15%	D	ND	ND	A	ND	ND	ND	A	A	ND	ND	ND	ND
Sodium Hypochlorite, 20%	D	D	D	A	ND	B	D	ND	A	ND	ND	ND	ND
Sodium Hypochlorite, concentrate	D	D	C	A	ND	B	D	ND	A	A	ND	ND	ND
Sodium Meta Phosphate	A	B	B	A	ND	A	ND	ND	A	ND	ND	ND	A
Sodium Nitrate	D	C	A	A	ND	D	ND	A	A	A	ND	ND	B
Sodium Nitrate, aqueous	A	ND	ND	A	ND	ND	ND	A	ND	ND	ND	ND	ND
Sodium Nitrite	ND	A	A	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Sodium Perborate	C	D	B	A	ND	B	ND	ND	A	ND	ND	ND	C




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Sodium Peroxide	C	D	B	A	ND	D	D	ND	A	ND	ND	ND	A
Sodium Phosphate	A	A	A	A	ND	ND	A	A	A	ND	ND	ND	ND
Sodium Salts	A	B	A	A	ND	A	A	ND	ND	ND	ND	ND	ND
Sodium Silicate	A	A	A	A	ND	ND	ND	ND	A	ND	ND	ND	B
Sodium Silicate, liquid	A	A	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Sodium Sulfate	A	A	A	A	ND	ND	A	ND	A	A	ND	ND	B
Sodium Sulfate, anhydrous	A	A	A	A	ND	A	A	ND	ND	ND	ND	ND	ND
Sodium Sulfide	A	A	A	A	ND	A	A	ND	A	A	ND	ND	B
Sodium Sulfite	A	A	A	A	ND	A	A	ND	A	A	ND	ND	ND
Sodium Thiosulfate	B	A	A	A	ND	A	A	ND	A	ND	ND	ND	A
Soybean Oil	A	C	C	A	ND	A	B	B	ND	ND	ND	ND	ND
Stannic Chloride	A	C	A	A	ND	B	B	ND	A	A	ND	ND	A
Stannic Chloride, 50%	A	C	C	A	ND	B	ND	ND	ND	ND	ND	ND	ND
Stannic Sulfide	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Stannous Chloride	A	C	A	A	ND	B	D	ND	A	A	ND	ND	ND
Stannous Chloride, 15%	A	C	A	A	ND	B	D	A	ND	ND	ND	ND	ND
Stannous Sulfide	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Starch	A	A	A	ND	A	ND	ND	ND	A	A	ND	ND	A
Stearic Acid	B	C	C	A	ND	B	A	A	A	A	ND	ND	B
Stoddard Solvent	B	D	D	A	A	D	A	ND	D	ND	A	A	A
Styrene	D	D	D	A	ND	D	C	C	ND	ND	ND	ND	A
Styrene-Monomer	D	D	D	A	ND	D	C	ND	ND	ND	ND	ND	ND
Sulfite Liquors	B	C	B	A	ND	D	ND	ND	A	ND	ND	ND	ND
Sulfonic Acid	D	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Sulfur	D	B	A	A	ND	B	B	A	A	B	ND	ND	ND
Sulfur Chloride	D	D	B	A	ND	C	ND	ND	A	ND	ND	ND	D
Sulfur Dioxide, dry	D	D	D	A	ND	B	ND	A	D	ND	A	A	B
Sulfur Dioxide, liquid	D	B	B	A	ND	B	ND	A	ND	ND	ND	ND	ND
Sulfur Dioxide, wet	D	C	C	A	ND	B	ND	ND	D	B	ND	ND	ND
Sulfur Hexa Fluoride	B	A	B	A	ND	B	ND	ND	ND	ND	ND	ND	ND
Sulfur Trioxide	D	D	D	A	ND	B	ND	ND	A	ND	ND	ND	C
Sulfuric Acid, 3 molar	D	C	B	A	ND	D	C	ND	ND	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Sulfuric Acid, 10%	A	B	B	A	B	D	C	A	A	A	D	D	C
Sulfuric Acid, 25%	C	B	B	A	B	D	C	A	A	A	ND	ND	ND
Sulfuric Acid, 30%	C	B	B	A	B	D	D	A	A	A	D	D	D
Sulfuric Acid, 50%	C	B	B	A	B	D	D	A	A	A	D	D	D
Sulfuric Acid, 60%	C	D	B	A	ND	D	D	A	A	B	D	ND	D
Sulfuric Acid, 70%	C	D	B	A	ND	D	D	A	A	B	D	ND	D
Sulfuric Acid, 75%	C	D	B	A	ND	D	D	A	A	C	D	ND	D
Sulfuric Acid, 80%	C	D	B	A	ND	D	D	A	A	C	D	ND	D
Sulfuric Acid, 85%	C	D	B	A	ND	D	D	A	C	D	D	ND	D
Sulfuric Acid, 90%	C	D	B	A	ND	D	D	A	C	D	D	ND	D
Sulfuric Acid, 95%	D	D	C	A	ND	D	D	B	D	D	D	A	D
Sulfuric Acid, 100%	D	D	D	A	ND	D	D	ND	D	ND	ND	ND	A
Sulfuric Acid, anhydride	C	C	C	A	ND	B	ND	ND	ND	ND	ND	ND	ND
Sulfuric Acid, concentrated	D	D	B	A	ND	D	D	ND	ND	ND	ND	ND	ND
Sulfuric Acid, dilute	D	B	B	A	ND	D	C	ND	ND	ND	ND	ND	ND
Sulfuric Acid, fuming	D	D	D	A	ND	D	D	C	ND	ND	ND	ND	ND
Sulfuric Acid, oleum	D	D	D	A	ND	D	D	C	ND	ND	ND	ND	ND
Sulfurous Acid	C	C	A	A	ND	ND	D	A	A	A	ND	ND	B
Sulfurous Acid, 10%	D	D	A	A	ND	D	D	ND	ND	ND	ND	ND	ND
Sulfurous Acid, 10% to 75%	D	D	A	A	ND	D	D	ND	ND	ND	ND	ND	ND
Sulfurous Acid, 100%	D	D	A	A	ND	C	D	ND	ND	ND	ND	ND	ND
Sulfurous Acid, anhydride	C	C	B	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Tall Oil	C	B	C	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Tallow	A	B	B	A	A	B	A	ND	ND	A	ND	ND	A
Tannic Acid	B	A	A	A	ND	B	A	A	A	A	ND	ND	C
Tartaric Acid	A	B	A	A	ND	A	A	A	A	A	ND	ND	B
Terpineol	B	D	D	A	ND	ND	B	ND	ND	ND	ND	ND	ND
Tertiary Butyl Alcohol	B	B	B	A	ND	B	D	ND	ND	ND	ND	ND	ND
Tetra Chloro Benzene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Tetra Chloro Ethane	D	D	D	A	ND	C	D	D	ND	ND	ND	ND	A
Tetra Chloro Ethylene	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND
Tetra Chloro Methane	C	D	D	A	ND	D	D	ND	ND	ND	ND	ND	ND




Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Tetra Chloro Napthalene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Tetra Ethyl Lead	C	C	D	A	ND	ND	ND	ND	A	ND	ND	ND	ND
Tetra Ethylene Glycol	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Tetra Hydro Furan	D	D	D	A	D	ND	C	B	D	C	C	A	A
Tetra Hydro Naphthalene	D	D	D	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Thionyl Chloride	ND	D	ND	A	ND	ND	ND	ND	D	D	ND	ND	ND
Tin Chloride	A	A	A	A	ND	A	B	ND	ND	ND	ND	ND	ND
Tin Salts	A	A	A	A	ND	B	B	ND	ND	ND	ND	ND	ND
Tin Tetra Chloride	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Titanium Tetra Chloride	C	D	D	A	ND	D	D	ND	D	ND	ND	ND	ND
Toluene	D	D	D	A	C	D	D	D	ND	C	A	A	A
Toluene Diisocyanate	D	D	D	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Transformer Oil	A	B	D	A	ND	B	D	ND	A	C	ND	ND	ND
Triacetin	B	B	B	A	ND	ND	D	ND	ND	ND	ND	ND	ND
Tributyl Amine	B	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Tributyl Phosphate	D	D	D	A	ND	ND	D	ND	D	ND	ND	ND	ND
Trichloro Benzene	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Trichloro Ethane	D	D	D	A	ND	D	D	ND	ND	ND	ND	ND	A
Trichloro Ethylene	D	D	D	A	ND	ND	D	D	ND	ND	ND	ND	ND
Trichloro Propane	D	C	D	A	ND	ND	ND	ND	A	ND	ND	ND	A
Tricresyl Phosphate	D	D	C	A	D	C	D	ND	ND	ND	ND	ND	A
Tridecanol	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Triethanol Amine	C	B	B	A	ND	ND	D	A	ND	ND	ND	ND	ND
Triethyl Amine	B	C	C	A	A	ND	ND	ND	A	ND	ND	ND	ND
Triethylene Glycol	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Trinitro Toluene	D	B	B	A	ND	C	ND	ND	ND	ND	ND	ND	ND
Trioctyl Phosphate	D	D	D	A	ND	C	D	ND	ND	ND	ND	ND	ND
Triphenyl Phosphate	D	ND	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Trisodium Phosphate	A	A	A	A	ND	ND	A	A	A	A	C	A	A
Tritolyl Phosphate	D	D	C	A	ND	C	D	ND	ND	ND	ND	ND	ND
Tung Oil	A	B	B	A	ND	D	C	B	ND	ND	ND	ND	ND
Turbine Oil	B	D	D	A	ND	D	A	ND	ND	ND	ND	ND	ND



Rubber Cal

3012 S. Croddy Way, Santa Ana, CA 92704
 Phone: (714)772-3000 (800) 370-9152
 Fax: (714)772-3088

Rating Code
 A=Excellent
 B=Good
 C=Fair
 D=Not Recommended
 ND=No Data

The information contained in this chemical resistance chart is for reference only. When multiple chemicals are in use, please refer to the most aggressive chemical when determining material suitability. Chemicals were tested at room temperature unless otherwise noted. The information contained in this chart does not constitute a warranty by Rubber-Cal for ducting products used in any specific application.

Chemical	Buna-N	Neoprene	Hypalon	Teflon	Acrylic	Silicone	Polyurethane	Santoprene (TPR)	PVC	Polyethylene (LLPE)	Aluminum	SS 304	SS 316
Turpentine	A	D	D	A	ND	D	D	D	A	C	A	A	A
Ucon-Hydrolube Oils	A	B	ND	A	ND	A	D	ND	ND	ND	ND	ND	ND
Undecanol	A	ND	A	A	ND	A	ND	ND	ND	ND	ND	ND	ND
Unsymmetrical Dimethyl Hydrazine	B	B	A	A	ND	D	ND	ND	ND	ND	ND	ND	ND
Uran	B	B	ND	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Urea	D	B	A	A	ND	ND	ND	A	A	A	ND	ND	ND
Varnish	B	D	D	A	ND	D	C	ND	ND	ND	ND	ND	ND
Versilube	A	A	A	A	ND	C	A	ND	ND	ND	ND	ND	ND
Vinegar	C	C	A	A	B	A	D	A	A	A	C	A	A
Vinyl Acetate	D	D	C	A	ND	ND	ND	ND	D	ND	ND	ND	ND
Vinyl Benzene	D	D	D	A	ND	D	C	ND	ND	ND	ND	ND	ND
Vinyl Chloride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Vinyl Ether	B	ND	B	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Vinyl Toluene	D	ND	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Vinyl Trichloride	D	D	D	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Water	A	B	A	A	A	A	C	A	A	ND	ND	ND	ND
Wax (Molten)	A	A	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Wood Alcohol	A	A	A	A	A	A	D	ND	ND	ND	ND	ND	ND
Xylene	D	D	D	A	C	D	D	D	D	C	A	A	A
Zeolites	B	C	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Zinc Acetate	B	B	C	A	ND	D	D	ND	ND	ND	ND	ND	ND
Zinc Carbonate	A	ND	A	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Zinc Chloride	A	A	A	A	ND	A	A	A	A	A	D	D	C
Zinc Chromate	A	A	C	A	ND	ND	ND	ND	ND	ND	ND	ND	ND
Zinc Nitrate	ND	ND	ND	ND	ND	ND	ND	ND	A	ND	ND	ND	ND
Zinc Salts	A	A	A	A	A	A	A	A	ND	ND	ND	ND	ND
Zinc Sulfate	A	A	A	A	ND	A	ND	A	ND	ND	ND	ND	ND

The ratings given in this chart are a consensus of available data. Be aware that this information is offered only as a guide. Performance in the field is influenced by temperature, media concentration, and other application variables. Performance and suitability can only be determined by user evaluation under actual service conditions. The Flexaust Company assumes no liability for the accuracy or completeness of the information presented. For chemicals not listed, contact us.